



GRT.0267

GROUT 6 HP SFR

Castable, structural concrete with controlled shrinkage for super anchorage

Customs Code

3824 5090

Packaging

- Bag 25 kg
- Pallet: 50 x (Bag 25 kg)

Application

- Pour out

Family
Grout

Product Lines

- Building
- Infratech
- Floor

Components
Single-component

Type
Structural free-flowing cement mortars

Functional Categories

- **Block repair of concrete works with free-flowing mortars**
- **Construction and maintenance interventions on airport runaways and quays**
- **Roads and municipal maintenance interventions**
- **Structural maintenance of dams, reservoirs, ducts and water ducts**
- **Structural maintenance of bridges and viaducts**
- **Structural maintenance of tunnels**
- **Structural precision anchoring**

Appearance
Powder

Certifications and legislations



EN 1504-3

Products and systems for the protection and repair of concrete structures - Structural and non-structural repair (R4)

General description

GROUT 6 HP SFR is a fibre-reinforced high-performance castable mortar, equipped with mechanical compressive and flexotraction resistance far superior to normal structural mortars. It is used for repairs, replenishments, strengthening concrete reinforcement and special works in FRC. The mix of special metal fibres (READYMESH MM-150) and synthetic fibres (READYMESH PM-060) is able to drastically reduce or even eliminate plastic-hygrometric shrinkage and the development of exceptional characteristics of ductility, fracture energy, resistance to shock and dynamic stress.

General features

With very low water-binder ratios, GROUT 6 HP SFR makes it possible to achieve compacting and hyperfluid rheologies that favour the movement of the mortar and the perfect filling of reinforced sprays, even with narrow spaces between the bars. The microsilica with pozzolanic activity increases the cohesion of the mixture with typical anti-segregating and anti-run-off effect. The particular fineness of the hydraulic binders contained in the formula promotes adherence to the substrate and has an effect of enlarging the fibrous components. The fibre mix offers strong ductility, toughness and flexotraction resistance to the castings performed with GROUT 6 HP SFR. With regard to the ANTICORROSIVE and PROTECTIVE FUNCTION ON THE REINFORCEMENT BARS, the main features of GROUT 6 HP SFR are:

- the mix of high-strength superfine binders, combined with very fine silicas with pozzolanic activities, to render the mortars intrinsically impermeable to water at the end of the hardening process;
- The strongly alkaline pH (> 12) protects the reinforcement bars from triggering corrosion;
- The negligible breathability of the carbon dioxide ensures hardened mortars with extremely prevalent anti-carbonation characteristics.

Overall, these anticorrosive specificities render the classic treatment of reinforcement bar passivation, preparatory to the pouring of castable mortar UNNECESSARY, provided that not too much time passes between the white metal cleaning operations and the castings of pourable mortar, at the risk of new oxidative processes being triggered. Thus, only in the event that long exposure times are foreseen between the bar-cleaning operations and the pouring of castable mortar is it advisable to treat with passivating slurry (REPAR MONOSTEEL or REPAR STEEL), applied by brush and only on the reinforcing bars.

Dosage

Approximately 21.00 kilograms/square metre of GROUT 6 HP SFR per centimetre of thickness to be realised (about 2100 kilograms per cubic metre).

IF YOU WANT TO SOLVE IT
 **azichem**

www.azichem.com

Updated: **26/11/2021**

General sales conditions and legal notices on

www.azichem.com/disclaimer

Fields of application

On-site castings or pumping carried out for any kind of structural replenishment of reinforced concrete, seismic reinforcement and adjustment, increases in cross-sectional resistance of concrete structures and masonry, anchorages of large-scale machinery (especially in the presence of significant dynamic stresses), anchoring of port bollards, deep-drawing and reinforcement works, restoration of highly-stressed industrial flooring both from a static and dynamic perspective, restoration of degraded foundations on bridges and viaducts especially whereby necessitating rapid reopening to vehicle traffic, construction of structures designed with HPC (High Performance Concrete) needs.

Basic features

 Max. recommended thickness: 20 cm	 Maximum diameter of aggregate: 6 mm
 Min. recommended thickness: 2.5 cm	 Mix with water: 10-11 %
 Pot-life: 30 min	 Shelf-life: 12 months
 Temperature of use: +5 / +35 °C	 Available colours Gray / Black

Technical specifications

Resistenza a trazione indiretta (EN 12390-6): > 6 N/mm²

Bonding force (UNI EN 1542): 3 N/mm²

Breaking load longitudinal (NTC 2018 § 11.2.10.2): > 5 N/mm²

Chloride content (UNI EN 1015-17): <0.01 %

Compressive strength after 01 day (UNI EN 1015-11): 50 N/mm²

Compressive strength after 07 days (UNI EN 1015-11): 85 N/mm²

Compressive strength after 28 days (UNI EN 1015-11): > 100 N/mm²

Density (UNI EN 1015-6): 2370 kg/m³

Flexural strength after 07 days (UNI EN 1015-11): 14 N/mm²

Flexural strength after 28 days (UNI EN 1015-11): 16 N/mm²

Flexural strength at 01 day (UNI EN 1015-11): 7 N/mm²

Reaction to fire (EN 13501-1): A1 _

Resistance to carbonatation (UNI EN 13295): 0.5 mm

Static elastic modulus (EN 13412): 35000 N/mm²

Tools cleansing

- Water

Applicable on

- Concrete
- Mixed walls (bricks and stones)
- Brickworks
- Stone walls
- Rusty reinforcement rods

Substrate preparation

Application surfaces must be clean, free of dust, contamination, crumbling, inconsistencies, etc., and adequately saturated-surface-dry with water. An adequate roughening of the surfaces by scarifying, sandblasting etc. is always necessary in order to obtain the maximum adhesion values to the substrate. The optimal values are obtained with high pressure hydro-scarification. Bare the irons undergoing disruptive oxidation or deeply oxidized, removing the rust of the exposed irons (by sandblasting or abrasive brushes).



www.azichem.com

Updated: 26/11/2021
General sales conditions and legal
notices on
www.azichem.com/disclaimer

Instructions for use

Mix the entire content of a bag of GROUT 6 HP SFR with effective vertical-axis mixers for at least 6 minutes, initially introducing a slightly reduced amount of water (9% = 2.25 litres/25 kilograms bag) compared to the required total water permitted (10%-12% = 2.5litres — 3.0 litres/25 kilogram bag) whilst mixing for at least 4 minutes. After this mixing time, evaluate the consistency of the mixture and, if necessary, gradually add in the last of the water until achieving the desired workability, without exceeding the limit of 12% (3.0 litres/25-kilogram bag), mixing at high RPM for at least another two minutes. For thick casting sections, it is advisable to add GHIAIETTO 6.10 (consult the relevant technical data sheet or ask for more information on the appropriate dosage of GHIAIETTO 6.10 from our technical service). Given the self-levelling properties of the product and its self-compacting capacity, paying due attention to the vibration phase is recommended. Excessive zeal in the vibration operation can worsen the aesthetic rendering of the end result. Do not use in the absence of suitable lateral containment. Ensure exposed surfaces are protected and wet-cured. Adopt casting procedures to ensure the absence of voids and discontinuities. Only pour the mortar from one part of the casting perimeter to avoid air pockets.

Storage and preservation

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.



Warnings, Precautions and Ecology

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.



www.azichem.com

Updated: **26/11/2021**
General sales conditions and legal notices on www.azichem.com/disclaimer

GROUT 6 HP SFR is produced/distributed by



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



www.azichem.com

Updated: **26/11/2021**
General sales conditions and legal
notices on
www.azichem.com/disclaimer